

# P-6

PLANETARY MILL

 FRITSCH

## TECHNICAL SPECIFICATIONS



EASY WORKING. GREAT RESULTS.



## **CONTENT**

Technical data .....	page 3
Accessories .....	page 5
Application examples .....	page 17



# TECHNICAL DATA

## P-6 – Planetary Mill

<b>Working principle</b>	impact force
<b>Material type</b>	hard, medium-hard, soft brittle, tough, moist
<b>Field of application</b>	geology and mineralogy metallurgy material technology ceramics pharmaceuticals chemistry biology sample preparation for analysis
<b>Working stations</b>	1 station
<b>Grinding tools</b>	grinding bowls + balls
<b>Materials grinding tools</b>	agate, hardened stainless steel, hardmetal tungsten carbide, sintered corundum, zirconium oxide, silicon nitride
<b>Grinding bowl sizes</b>	12 ml, 45 ml (with adapter) 80 ml, 250 ml, 500 ml
<b>Grinding ball sizes</b>	1 – 40 mm
<b>Max. initial size / feeding size</b>	10 mm
<b>Sample quantity</b>	0.5 – 225 ml
<b>Final fineness</b> <i>(depends on application)</i>	< 1 µm colloidal grinding
<b>Average grinding time to analytical fineness</b>	4 min
<b>Grinding process</b>	dry/wet
<b>Grinding in inert gas</b> <i>(Additional lock-system required)</i>	yes
<b>Gas pressure and temperature measurement</b>	yes
<b>Rotational speed of main disk</b>	100 – 650 rpm



<b>Transmission ratio planetary disk/grinding bowl</b>	$i_{\text{relative}} = 1 : -1.82$
<b>Relative bowl speed</b>	1,183 rpm
<b>Effective diameter of main disk</b>	121.6 mm
<b>Centrifugal acceleration (<math>g = 9.81 \text{ m/s}^2</math>)</b>	29 g
<b>Interface</b>	yes
<b>Power consumption</b>	1,000 W
<b>Electrical details</b>	100 – 120 / 200 – 240 V/1; 50 – 60 Hz
<b>Emission sound pressure level at the workplace acc. to DIN EN ISO 3746 (workplace related)</b>	up to approx. $L_{pAd} = 85 \text{ dB}$
<b>Weight</b>	63 kg
<b>Safety class</b>	IP21
<b>Dimensions (W x D x H)</b>	benchtop 37 x 53 x 50 cm

---



# ACCESSORIES

## P-6 – Planetary Mill

Order no.

Article



**Instrument without grinding bowls and balls, incl. Safe-Lock clamping system**

06.2000.00

for 100 – 120 / 200 – 240 V/1~, 50 – 60 Hz, 1,000 W


*Voltage indicated by customer is set*

### Certification

96.0240.00

IQ/OQ documentation

*(Questionnaire format – implementation not included)*



*Imbalance compensation through simple compensation mechanism*



Order no.

Article



## Grinding bowls for Planetary Mill P-6

### Grinding bowls with lid and seal ring

#### Grinding bowls 500 ml volume

50.1055.00	Agate, with steel casing
50.1060.00	Sintered corundum (99.7 % $\text{Al}_2\text{O}_3$ )
50.1110.00	Zirconium oxide
50.1090.00	Hardened, stainless steel
50.1310.00	Silicon nitride, with steel casing
50.2661.20	Replacement seal ring PTFE 121/110 mm dia. for agate bowls of 500 ml volume
50.1010.20	Replacement seal ring PTFE 110/101 mm dia. for silicon nitride bowls of 500 ml volume
50.1230.20	Replacement seal ring PTFE 116/100 mm dia. for all other bowls of 500 ml volume

#### Grinding bowls 250 ml volume

50.2055.00	Agate, with steel casing
50.2060.00	Sintered corundum (99.7 % $\text{Al}_2\text{O}_3$ )
50.2110.00	Zirconium oxide
50.2090.00	Hardened, stainless steel
50.2080.00	Hardmetal tungsten carbide, with steel casing
50.2310.00	Silicon nitride, with steel casing
50.2011.20	Replacement seal ring PTFE 85/70 mm dia. for agate bowls of 250 ml volume
50.2010.20	Replacement seal ring PTFE 85/76 mm dia. for silicon nitride bowls of 250 ml volume



Order no.	Article
50.2230.20	Replacement seal ring PTFE 90/75 mm dia. for all other bowls of 250 ml volume
<b>Grinding bowls 80 ml volume</b>	
50.4055.00	Agate, with steel casing
50.4060.00	Sintered corundum (99.7 % Al <sub>2</sub> O <sub>3</sub> )
50.4110.00	Zirconium oxide
50.4090.00	Hardened, stainless steel
50.4080.00	Hardmetal tungsten carbide, with steel casing
50.4310.00	Silicon nitride
50.2011.20	Replacement seal ring PTFE 85/70 mm dia. for agate bowls of 80 ml volume
50.4230.20	Replacement seal ring PTFE 80/65 mm dia. for all other bowls of 80 ml volume
90.1120.09	Adapter for grinding bowls 12 ml, 45 ml, 80 ml volume <i>(Essential, if only one grinding bowl is inserted in the grinding bowl holder)</i>
<b>Grinding bowls 45 ml volume for P-6</b>	
50.7050.00	Agate
50.7060.00	Sintered corundum (99.7 % Al <sub>2</sub> O <sub>3</sub> )
50.7110.00	Zirconium oxide
50.7090.00	Hardened, stainless steel
50.7080.00	Hardmetal tungsten carbide, with steel casing
50.7310.00	Silicon nitride
50.7250.20	Replacement seal ring PTFE 50/40 mm dia. for all bowls of 45 ml volume
<b>Grinding bowls 12 ml volume for P-6</b>	
50.5050.00	Agate
50.5060.00	Sintered corundum (99.7 % Al <sub>2</sub> O <sub>3</sub> )
50.5110.00	Zirconium oxide



Order no.	Article
<b>Grinding bowls 12 ml volume for P-6</b>	
50.5090.00	Hardened, stainless steel
50.5080.00	Hardmetal tungsten carbide
50.5310.00	Silicon nitride
50.5250.20	Replacement seal ring PTFE 37/26 mm dia. for all bowls of 12 ml volume
90.1120.09	Adapter for grinding bowls 12 ml, 45 ml, 80 ml volume for P-6 <i>(Essential, if only one grinding bowl 80 ml volume per grinding bowl holder or if grinding bowls 12 ml resp. 45 ml are inserted into the P-6)</i>

### **Accessories for single-use technology for P-6**

50.3200.00	Aluminium grinding bowl, modified to customer specifications, for use with tubes
50.3010.00	Aluminium grinding bowl with 8 x 20 ml tubes



To specifically prevent contamination of samples due to unwanted abrasion, all grinding bowls and the corresponding grinding balls are available in 6 different materials.



Order no.

Article



## EasyGTM – Gas pressure and temperature measuring system for Planetary Mill P-6

### EasyGTM for continuous measurement of gas pressure and temperature

50.2480.00 incl. 250 ml grinding bowl made of hardened, stainless steel with special lid, transmitter, separate receiver and software EasyGTMControl

50.2490.00 incl. 500 ml grinding bowl made of hardened, stainless steel with special lid, transmitter, separate receiver and software EasyGTMControl

*If further grinding bowls and transmitters are needed, please ask for the respective order numbers.*



With the new EASY GTM gas pressure and temperature measurement system, you can transform your P-6 planetary mill into an analytical measurement system.



Order no.

Article



## Gassing lids for Planetary Mill P-6

### Accessories for grinding in inert gas and for mechanical alloying

#### Gassing lids with 2 valves and seal ring for grinding bowls 500 ml volume

50.8010.00	Agate, with steel casing
50.9100.00	Zirconium oxide
50.8400.00	Hardened, stainless steel
50.9150.00	Silicon nitride, with steel casing
50.8013.16	Replacement seal ring made of Viton for gassing lid for agate bowls 500 ml volume
50.1230.16	Replacement seal ring made of Viton for gassing lid for all other bowls 500 ml volume

#### Gassing lids with 2 valves and seal ring for grinding bowls 250 ml volume

50.8100.00	Agate, with steel casing
50.8950.00	Zirconium oxide
50.8500.00	Hardened, stainless steel
50.8600.00	Hardmetal tungsten carbide, with steel casing
50.8900.00	Silicon nitride, with steel casing
50.2011.16	Replacement seal ring made of Viton for gassing lid for agate bowls 250 ml volume
50.2010.16	Replacement seal ring made of Viton for gassing lid for silicon nitride bowls 250 ml volume
50.2230.16	Replacement seal ring made of Viton for gassing lid for all other bowls 250 ml volume

#### Gassing lids with 2 valves and seal ring for grinding bowls 80 ml volume

50.8100.00	Agate, with steel casing
50.8840.00	Zirconium oxide



Order no.	Article
50.8700.00	Hardened, stainless steel
50.8880.00	Hardmetal tungsten carbide, with steel casing
50.2011.16	Replacement seal ring made of Viton for gassing lid for agate bowls 80 ml volume
50.4230.16	Replacement seal ring made of Viton for gassing lid for all other bowls 80 ml volume
90.1400.00	Additional lock-system for all grinding bowls 500 ml, 250 ml, 80 ml volume (for the transport of the closed grinding bowl)

*Gassing lids with Swagelok valves are available on request.*



*By using a special lid on the grinding bowl, you can also grind your samples under protective gas and mechanically alloy/activate them.*



Order no.

Article



## Grinding balls for Planetary Mill P-6

### Grinding balls 40 mm dia. for grinding bowls 500 ml

55.0400.06 Sintered corundum (99.7 %  $Al_2O_3$ )

55.0400.27 Zirconium oxide

55.0400.09 Hardened, stainless steel

55.0400.31 Silicon nitride

### Grinding balls 30 mm dia. for grinding bowls 500 ml, 250 ml

55.0300.05 Agate, polished

55.0300.06 Sintered corundum (99.7 %  $Al_2O_3$ )

55.0300.27 Zirconium oxide

55.0300.09 Hardened, stainless steel

55.0300.08 Hardmetal tungsten carbide

55.0300.31 Silicon nitride

### Grinding balls 20 mm dia. for grinding bowls 500 ml, 250 ml, 80 ml

55.0200.05 Agate, polished

55.0200.06 Sintered corundum (99.7 %  $Al_2O_3$ )

55.0200.27 Zirconium oxide

55.0200.09 Hardened, stainless steel

55.0200.08 Hardmetal tungsten carbide

55.0200.31 Silicon nitride

### Grinding balls 15 mm dia. for grinding bowls 500 ml, 250 ml, 80 ml, 45 ml

55.0150.05 Agate, polished

55.0150.06 Sintered corundum (99.7 %  $Al_2O_3$ )

55.0150.27 Zirconium oxide



Order no.	Article
55.0150.09	Hardened, stainless steel
55.0150.08	Hardmetal tungsten carbide
55.0150.31	Silicon nitride
	<b>Grinding balls 10 mm dia. for grinding bowls 500 ml, 250 ml, 80 ml, 45 ml, 12 ml</b>
55.0100.05	Agate, polished
55.0100.06	Sintered corundum (99.7 % Al <sub>2</sub> O <sub>3</sub> )
55.0100.27	Zirconium oxide
55.0100.09	Hardened, stainless steel
55.0100.08	Hardmetal tungsten carbide
55.0100.31	Silicon nitride
	<b>Grinding balls 5 mm dia. for grinding bowls 500 ml, 250 ml, 80 ml, 45 ml, 12 ml</b>
55.0050.05	Agate, polished (100 pieces weigh approx. 17 g) <sup>1)</sup>
55.0050.06	Sintered corundum (99.7 % Al <sub>2</sub> O <sub>3</sub> ) (100 pieces weigh approx. 48 g) <sup>1)</sup>
55.0050.27	Zirconium oxide (100 pieces weigh approx. 38 g) <sup>1)</sup>
55.0050.09	Hardened, stainless steel (100 pieces weigh approx. 52 g) <sup>1)</sup>
55.0050.08	Hardmetal tungsten carbide (100 pieces weigh approx. 97 g) <sup>1)</sup>
55.0050.31	Silicon nitride (100 pieces weigh approx. 48 g) <sup>1)</sup>
	<sup>1)</sup> The number of balls per grinding bowl can be calculated by weighing using the weight specification.
	<b>Grinding balls ≤ 3 mm dia. for grinding bowls 500 ml, 250 ml, 80 ml, 45 ml, 12 ml</b>
55.0030.27	Zirconium oxide 3 mm dia.
55.0020.27	Zirconium oxide 2 mm dia.
55.0015.27	Zirconium oxide 1.5 mm dia.
55.0010.27	Zirconium oxide 1 mm dia.
55.0005.27	Zirconium oxide 0.5 mm dia.



Order no.

Article

**Grinding balls  $\leq$  3 mm dia. for grinding bowls 500 ml, 250 ml, 80 ml, 45 ml, 12 ml**

55.0001.27	Zirconium oxide 0.1 mm dia.
55.0030.09	Hardened, stainless steel 3 mm dia.
55.0010.09	Hardened, stainless steel 1 mm dia.
55.0030.08	Hardmetal tungsten carbide 3 mm dia.
55.0016.08	Hardmetal tungsten carbide 1.6 mm dia.
55.0006.08	Hardmetal tungsten carbide 0.6 mm dia.

*Further grinding balls  $\leq$  3 mm dia. are available.  
Grinding balls also available in further sizes.*



*By selecting the size of the grinding balls, you can optimally adjust the grinding process to each individual application.*



## Material data grinding bowls/grinding balls

Material	Main component of the material*	Density g/cm <sup>3</sup>	Abrasion resistance	Sample material
Agate	SiO <sub>2</sub>	2.65	good	soft to medium-hard samples
Sintered corundum	Al <sub>2</sub> O <sub>3</sub>	3.8	fairly good	medium-hard, fibrous samples
Silicon nitride	Si <sub>3</sub> N <sub>4</sub>	3.25	extremely good	abrasive samples, metal-free grinding
Zirconium oxide	ZrO <sub>2</sub>	5.7	very good	fibrous, abrasive samples
Hardened stainless steel	Fe – Cr	7.7	good	hard, medium-hard, brittle samples
Hardmetal tungsten carbide	WC	14.3	very good	hard, abrasive samples

\* At [www.fritsch.de](http://www.fritsch.de), you will find the standard analyses with detailed information on the materials directly next to the respective grinding bowls and balls.

## Recommended grinding ball size

Application	Suitable ball diameter
Maximum feed size 10 mm	30 mm or 40 mm
Average feed size ≤ 5 mm	20 mm, 15 mm or 10 mm
Fine material ≤ 0.5 mm	10 mm or smaller
Homogenising dry or liquid samples	20 mm, 10 mm or smaller
Homogenising viscous samples	20 mm or 15 mm

The specified grinding ball sizes are application-dependent guidelines. It is not recommended to mix balls with different diameters.

Grinding balls with a diameter of 40 mm should only be used for short grinding times.



## Recommended filling per grinding bowl

### Grinding balls $\geq 5$ mm: Recommended number of balls per grinding bowl

Grinding bowl		12 ml	45 ml	80 ml	250 ml	500 ml
Useful capacity (sample volume)		0.5 – 5 ml	3 – 20 ml	10 – 35 ml	30 – 125 ml	80 – 225 ml
Balls diameter	5 mm	50	180	250	1200	2000
	10 mm	6	18	25	50	100
	15 mm	–	7	10	45	70
	20 mm	–	–	5	15	25
	30 mm	–	–	–	6	8
	40 mm	–	–	–	–	4

### Grinding balls $\leq 3$ mm: Recommended ball mass per grinding bowl in grams

Grinding bowl		12 ml	45 ml	80 ml	250 ml	500 ml
Useful capacity (sample volume)		0.5 – 5 ml	3 – 20 ml	10 – 35 ml	30 – 125 ml	80 – 225 ml
Material	Zirconium oxide	20 g	70 g	100 g	400 g	800 g
	Hardened, stainless steel	30 g	90 g	150 g	500 g	1100 g
	Hardmetal tungsten carbide	50 g	200 g	300 g	1000 g	2100 g

**i** Grinding balls with a diameter of 3 mm and smaller must be weighed. The above table shows the required weight per grinding bowl.

The usable capacity depends on the type of material.

The specified ball filling per bowl is the minimum quantity; depending on the material behaviour, it may need to be increased.

In exceptional cases, the quantity of grinding balls can be reduced by up to 15 %. In order to achieve consistent grinding results in line with our recommendations, a longer grinding time is necessary, which may result in increased abrasion.



# APPLICATION EXAMPLES

## P-6 – Planetary Mill

### Sample 1: silicon carbide

#### Milling:

- 80 ml tungsten carbide grinding bowl
- 5 x 20 mm grinding balls
- 200 rpm
- 30 sec



### Sample 2: paper

#### Milling:

- 250 ml sintered corundum grinding bowl
- 6 x 30 mm grinding balls
- 200 rpm
- 2 min





### Sample 3: basalt

#### Milling:


- 250 ml steel grinding bowl
- 15 x 20 mm grinding balls
- 200 rpm
- 2 min



### Sample 4: acrylic paint

#### Mixing:

- 80 ml zirconium oxide grinding bowl
- 5 x 10 mm grinding balls
- 200 rpm
- approx. 1 min





**FRITSCH GmbH**  
**Industriestraße 8**  
**55743 Idar-Oberstein**  
**+49 67 84 70 0**  
**[www.fritsch.de](http://www.fritsch.de)**  
**[service@fritsch.de](mailto:service@fritsch.de)**

*Contact person:*

**Contact us now**

for a non-binding consultation or individual test grinding to identify your ideal device configuration and optimal grinding parameters.



